



Technical Data Sheet

LINTEC - PRIME CAST COATED PAPER (J) PW 6LY

Product Description

LINTEC - PRIME CAST COATED PAPER (J) PW 6LY is premium self-adhesive material with a mirror finish white cast coated paper face stock. Combining excellent print and image definition, LINTEC - PRIME CAST COATED PAPER (J) PW 6LY is perfect for high quality printed labels using digital offset printers; and available with permanent adhesives to suit your needs.

Product Features

High Gloss for Excellent Ink Link, Crisp Die-Cutting Properties

Application

For General Label (Permanent Type)

Technical Data Specification

Product Construction	Type
Face Material	Cast Coated Paper White 80
Adhesive type	Acrylic Adhesive
Release Liner	One Side PE Laminated Woodfree Paper Yellow With Silicone Coating

Test Items		Unit	Average Value	Test Method
Thickness	Face	μm	81	JIS P 8118
	Release	μm	93	JIS P 8118
Grammage	Face	g/m ²	80.2	JIS P 8124
Adhesion (After 30 min)		SI	B 20 . 0	LINTEC Standard
Adhesion (After 24 hrs)		SI	B 21 . 0	LINTEC Standard
Holding Power (sec)		-	NC 30,000	LINTEC Standard
Ball Tack (No.)		-	6	J DOW

Remarks:

Unit for Adhesion	:	SI; N/25mm
B	:	Break
NC	:	Non Creep
Holding Power Test Method	:	0° Dead Load Test at 40°C, Applied area of 25mm X 25mm, substrate is stainless steel, with the rubber roll 2kg with press back and forth for 5 times, still weight is 9.8N (1000gf)

PT. Multi Viscomindo

Jl. Deplu Raya No. 7, Bintaro, Pesanggrahan – Jakarta 12330

Tel: +62 21 7376530 – Fax: +62 21 7363488

Email: sales@multiviscomindo.com



Storage Condition:

1. Avoid storage in places with high humidity and high temperature.
Ideal condition: Temperature ; 10°C ~ 30°C, Humidity ; < 70%RH.
2. Contact with water and chemical must be avoided.
3. Polyethylene film packaging is recommended for longer shelf life.
4. Direct exposure to the sunlight must be avoided and distance must be kept from the light source.
5. To ensure a longer shelf life, sheets must be stored in a laying position.
6. Avoid causing any form of impact on the material.

The statements in this information sheet are based upon our knowledge and practical experience. This data is intended only as a source of information and is given without guarantee and does not constitute a warranty. Due to the wide variety of possible uses and applications, customers should independently determine the suitability of this material for their specific purpose, prior to use.

PT. Multi Viscomindo

Jl. Deplu Raya No. 7, Bintaro, Pesanggrahan – Jakarta 12330

Tel: +62 21 7376530 – Fax: +62 21 7363488

Email: sales@multiviscomindo.com